

PA152尼龙粉硅胶烫画粉

Pa152 nylon powder, silicone hot painting powder



产品参数 Product parameters		高温粉 (进口材料) High temperature powder (imported material)		
型号 Model	纯PA152热熔粉 Pure PA152 hot melt powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	120	外观 appearance	透明粉末 Transparent powder	
熔指 Melting fingers	35	粒径范围 Particle size range	80-170pm	
压烫条件 Pressing conditions	时间 Time	12-8s	20℃水洗 Wash with water at 20℃	4
	温度 temperature	150-160℃	40℃水洗 Wash with water at 40℃	4
	压力 pressure	4kg	干洗 dry cleaning	4
功能用途 Functional use	后唛、织带、氨纶面料、牛仔、硅胶粉、重水洗专用。 Rear mark, webbing, spandex fabric, denim, silicone powder, heavy washing.			

P168粉皮革/牛津布专用


P168 Pink leather/Oxford cloth exclusive



产品参数 Product parameters		中温粉 (进口材料) Medium temperature powder (imported material)		
型号 Model	PES168热熔粉 PES168 hot melt powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	105-110	外观 appearance	粉末 powder	
熔指 Melting fingers	30	粒径范围 Particle size range	80-170pm	
压烫条件 Pressing conditions	时间 Time	8-12s	40℃水洗 Wash with water at 40℃	4
	温度 temperature	140-160℃	60℃水洗 Wash with water at 60℃	2
	压力 pressure	4kg	干洗 dry cleaning	4
功能用途 Functional use	皮革、牛津布、无纺布、纺布袋、低端产品专用粉。 Leather, oxford fabric, non-woven fabric, woven bag, special powder for low-end products.			

T161低温粉

T161 low temperature powder



产品参数 Product parameters		低温粉 (进口材料) Low temperature powder (imported material)		
型号 Model	纯TPU161粉 Pure TPU161 powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	85-95	外观 appearance	透明粉末 Transparent powder	
熔指 Melting fingers	25	粒径范围 Particle size range	80-160pm	
压烫条件 Pressing conditions	时间 Time	12s	40℃水洗 Wash with water at 40℃	4
	温度 temperature	110-150℃	60℃水洗 Wash with water at 60℃	4
	压力 pressure	3-4kg	干洗 dry cleaning	4
功能用途 Functional use	面料在120℃高温压烫缩水专用，压烫无压痕，不变色。 The fabric is specially pressed and shrunk at 120℃, and it is pressed without indentation and does not change color.			

● EVA、热熔粉，低熔点，面料定型，EVA鞋材专用

EVA, hot melt powder, low melting point, fabric shaping, EVA shoe material special

● PES178衫布，无纺布、帆布，低端产品专用粉

PES178 shirt cloth, non-woven fabric, canvas, special powder for low-end products

● P80 网印硅胶烫画专用粉

P80 screen printing silicone hot painting powder

● T60 丝网印刷烫金专用粉

T60 screen printing bronzing powder

● T200 植绒烫画专用粉

T200 Flocking hot painting powder

● T99 无手感透气热熔粉配合透气白墨一起使用

T99 Handsless Breathable Hot Melt Powder is used with breathable white ink

● T300 高厚、高柔热熔粉，圆角立体感强

T300 high thickness, high soft hot melt powder, rounded corners strong three-dimensional feeling


● T400 3D热熔粉 直角有立体厚感

T400 3D hot melt powder has a three-dimensional thick feeling at right angles



T183热熔粉


T183 hot melt powder



产品参数		中温粉 (国产材料)		
Product parameters		Medium temperature powder (domestic material)		
型号 Model	纯TPU183热熔粉 Pure TPU183 hot melt powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	105-110	外观 appearance	透明粉末 Transparent powder	
熔指 Melting fingers	30	粒径范围 Particle size range	120-250pm	
压烫条件 Pressing conditions	时间 Time	12-8s	耐洗性能 Washable resistance	
	温度 temperature	140-160°C		40°C水洗 Wash with water at 40°C
	压力 pressure	4kg		60°C水洗 Wash with water at 60°C
			4	
			3	
			4	
功能用途 Functional use	物美价廉, 帆布针织布, 常规面料, 通用型用粉。 Inexpensive, canvas knitted fabric, conventional fabric, universal powder.			

T171防静电热熔粉


T171 anti-static hot melt powder



产品参数		中温粉 (进口材料)		
Product parameters		Medium temperature powder (imported material)		
型号 Model	纯TPU171热熔粉 Pure TPU171 hot melt powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	105-110	外观 appearance	透明粉末 Transparent powder	
熔指 Melting fingers	30	粒径范围 Particle size range	100-230pm	
压烫条件 Pressing conditions	时间 Time	12-8s	耐洗性能 Washable resistance	
	温度 temperature	140-160°C		40°C水洗 Wash with water at 40°C
	压力 pressure	4kg		60°C水洗 Wash with water at 60°C
			4	
			3	
			4	
功能用途 Functional use	完全防静电, 抖粉干净, 花位边缘不粘粉, 不挑膜 Completely anti-static, clean shaking powder, non-sticky powder on the edge of the flower position, no picking			

T173热熔粉常规细粉


T173 hot melt powder conventional fine powder



产品参数		中温粉 (国产材料)		
Product parameters		Medium temperature powder (domestic material)		
型号 Model	纯TPU173粉 Pure TPU173 powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	105-110	外观 appearance	透明粉末 Transparent powder	
熔指 Melting fingers	30	粒径范围 Particle size range	80-170pm	
压烫条件 Pressing conditions	时间 Time	12-6s	耐洗性能 Washable resistance	
	温度 temperature	150-160°C		40°C水洗 Wash with water at 40°C
	压力 pressure	4kg		60°C水洗 Wash with water at 60°C
			4	
			3	
			4	
功能用途 Functional use	常规性面料通用, 重硅油面料, 测试水再使用 Conventional fabrics are universal, heavy silicone oil fabrics, test water reuse			

T141防静电高弹粉

T141 anti-static high elastic powder




产品参数		中温粉 (进口材料)		
Product parameters		Medium temperature powder (imported material)		
型号 Model	纯TPU141粉 Pure TPU141 powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	105-110	外观 appearance	透明粉末 Transparent powder	
熔指 Melting fingers	30	粒径范围 Particle size range	90-180pm	
压烫条件 Pressing conditions	时间 Time	12-8s	耐洗性能 Washable resistance	
	温度 temperature	150-160°C		40°C水洗 Wash with water at 40°C
	压力 pressure	4kg		60°C水洗 Wash with water at 60°C
			4	
			3	
			4	
功能用途 Functional use	防静电、不粘粉、不挑膜, 高回弹、手感柔、适合面料广、小字母效果OK。 Anti-static, non-sticky, non-picking, high rebound, soft feeling, suitable for a wide range of fabrics, Small letter effect OK.			

T210高弹防油秒撕粉

T210 high elasticity oil resistance second tear powder

DTF烫画主力产品

DTF hot painting main product



产品参数		高温粉 (进口材料)		
Product parameters		High temperature powder (imported material)		
型号 Model	纯TPU210热熔粉 Pure TPU210 hot melt powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	120	外观 appearance	透明粉末 Transparent powder	
熔指 Melting fingers	30	粒径范围 Particle size range	100-220pm	
压烫条件 Pressing conditions	时间 Time	12-8s	耐洗性能 Washable resistance	
	温度 temperature	145-160°C		40°C水洗 Wash with water at 40°C
	压力 pressure	4kg		60°C水洗 Wash with water at 60°C
			4	
			3	
			4	
功能用途 Functional use	销冠产品, 防返油、成膜快、助秒撕、提高产能、抖粉干净, 欧美畅销产品。 Pinguan products, anti-oil return, fast film formation, second tearing, improve production capacity, shake powder clean. Best-selling products in Europe and the United States.			

T98超柔BB粉细纹面料专用

T98 super soft BB pink fine grain fabric exclusive




产品参数		高温粉 (进口材料)		
Product parameters		High temperature powder (imported material)		
型号 Model	纯T98热熔粉 Pure T98 hot melt powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	115-120	外观 appearance	透明粉末 Transparent powder	
熔指 Melting fingers	30	粒径范围 Particle size range	60-110pm	
压烫条件 Pressing conditions	时间 Time	12-8s	耐洗性能 Washable resistance	
	温度 temperature	150-160°C		40°C水洗 Wash with water at 40°C
	压力 pressure	4kg		60°C水洗 Wash with water at 60°C
			4	
			3	
			4	
功能用途 Functional use	泳装: 超细面料烫画无厚感, 手感柔软, 耐拉, 回弹强 Swimwear: ultra-fine fabric hot painting without thick feeling, soft hand feeling, pull resistance, strong rebound			

P152-5防升华白粉

P152-5 anti-sublimation white powder

T143防升华黑粉


T143 anti-sublimation black powder



产品参数		低温粉		
Product parameters		Low temperature powder		
型号 Model	P152-5防升华白粉 P152-5 anti-sublimation white powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	100-105	外观 appearance	粉末 powder	
熔指 Melting fingers	30	粒径范围 Particle size range	80-160pm	
压烫条件 Pressing conditions	时间 Time	12-15s	耐洗性能 Washable resistance	
	温度 temperature	145-150°C		40°C水洗 Wash with water at 40°C
	压力 pressure	4kg		60°C水洗 Wash with water at 60°C
			4	
			3	
			4	
功能用途 Functional use	用于掉色面料导致图案变色, 根据确认面料, 测试OK, 再生产大货。 It is used to discolor the fabric and cause the pattern to change color, according to the confirmation of the fabric, test OK, and then produce large goods.			

T176高弹防油秒撕粉

T176 high elasticity oil resistant second tear powder



产品参数		高温粉 (进口材料)		
Product parameters		High temperature powder (imported material)		
型号 Model	纯TPU176热熔粉 Pure TPU176 hot melt powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	110-120	外观 appearance	透明粉末 Transparent powder	
熔指 Melting fingers	30	粒径范围 Particle size range	100-200pm	
压烫条件 Pressing conditions	时间 Time	12-6s	耐洗性能 Washable resistance	
	温度 temperature	150-160°C		40°C水洗 Wash with water at 40°C
	压力 pressure	4kg		60°C水洗 Wash with water at 60°C
			4	
			4	
			4	
功能用途 Functional use	高回弹、防返油、放回潮、粘合力粘秒撕, 尖角不翘边, 防回潮 High rebound, anti-rejuvenation, moisture restoration, adhesion sticking second tear, sharp corners without warping, anti-moisture			

T99无手感透气热熔粉


T99 breathable hot melt powder without hand feeling



产品参数		高温粉 (进口材料)		
Product parameters		High temperature powder (imported material)		
型号 Model	纯T99热熔粉 Pure T99 hot melt powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	120	外观 appearance	粉末 powder	
熔指 Melting fingers	30	粒径范围 Particle size range	60-120pm	
压烫条件 Pressing conditions	时间 Time	12-8s	耐洗性能 Washable resistance	
	温度 temperature	150-160°C		40°C水洗 Wash with water at 40°C
	压力 pressure	4kg		60°C水洗 Wash with water at 60°C
			4	
			3	
			4	
功能用途 Functional use	透气热熔粉, 直裂热熔粉, 针对透气产品专用, 结合W13白墨一起使用, 完全透气, 无手感。 Breathable hot melt powder, straight split hot melt powder, special for breathable products, combined with W13 white ink used together, completely breathable, no hand feeling.			

TPU100粉户外用品专用

TPU100 powder for outdoor products



产品参数		超低温粉		
Product parameters		Ultra-low temperature powder		
型号 Model	纯TPU100热熔粉 Pure TPU100 hot melt powder	成份 ingredient	聚氨酯 polyurethane	
熔融范围 Melting range	75-80	外观 appearance	透明粉末 Transparent powder	
熔指 Melting fingers	20	粒径范围 Particle size range	80-170pm	
压烫条件 Pressing conditions	时间 Time	20-10s	耐洗性能 Washable resistance	
	温度 temperature	100°C		30°C水洗 Wash with water at 30°C
	压力 pressure	4kg		40°C水洗 Wash with water at 40°C
			3.5	
			3	
			3.5	
功能用途 Functional use	不耐温面料, 空气层面料, 真皮海绵帽片。 Heat-resistant fabric, air-layer fabric, leather sponge cap sheet.			