


Brand name	UV label AB film		
Product structure		→ Facing material → glue → substrate	
Facing material			
Material name	PET	thickness (mm)	0.025±0.002
Basis weight (g/m ²)	35±2	colour	transparent
Material name	PET	Thickness (mm)	0.075±0.002
Basis weight (g/m ²)	105±3	colour	transparent
Viscose glue			
Test item	Standard value	unit	Test method
Coating thickness	0.025±0.003	mm	GB-01
Amount of glue (dry glue)	26±3	g/m ²	GB-02
Adhesion of mirror steel	1800 ↑	g/25.4mm	GB/T 2792-1998 (Longitudinal sampling)
Grinding steel adhesion	~~	kg/inch	GB/T 2792-1998 (Longitudinal sampling)
Initial force	1 ↑	#	GB/T 4852
retentivity	24h	hr/kg×inch ²	GB/T 4851

Applicable temperature	-20~75	°C	~~
Storage condition	<p>Storage conditions are normal temperature, cool ventilated dry place (0~28°C, 70%RH below), avoid high temperature and humidity, do not sun and rain. The optimal storage condition is 23±5°C, 65± 5%RH, and the shelf life is 12 months. Note: If the temperature and humidity of the product are too high or too low for a long time, it will lead to quality preservation (The deadline was significantly shortened.)</p>		